


Primary Lithium Battery

CP505050

3.0V [Li-MnO₂]



BENEFITS

- High voltage response, stable during most of the lifetime of the application
- Energy Density up to 830Wh/L
- Wide operating temperature range(-40 °C ~+70 °C)
- Low Self-discharge Rate(less than 2% per year of storage at +20°C)

KEY FEATURES

- Optimized battery structure,full discharge capacity
- Super long endurance
- No passivation
- GB 8897.4-2008、 IEC 60086.4:2014 and RoHS
- Easy to recover

MAIN APPLICATIONS

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

Cell References Data

Electrical characteristics

Open circuit voltage (at 23±2°C) **≥3.10V**

Nominal capacity **3000mAh**

(At +25°C,battery discharged at continuous current 10mA until voltage reaches cut-off voltage 2.0V. The capacity can vary at different temperature, discharge current or cut-off voltage.)

Maximum continuous current **1500mA**

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity.)

Maximum pulse discharge current **2000mA**

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. The discharged capacity may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult HCB.)

Storage (recommended) **≤+30°C**

(for more severe conditions. Consult HCB) **≤75%RH**

Operating temperature range **-40°C~+70°C**

(Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult HCB)

HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040

Tel: +86(0)27 83248452

Fax: +86(0)27 83248455

Email: haocheng@cnhcb.com

Web: www.cnhcb.com

No.: HCB-MKT.PM-S[V2.0 2018 02]

Primary Lithium Battery

CP505050


3.0V [Li-MnO₂]

Physical characteristics

Width (max)	50.0mm
Height (max)	51.0mm
Thickness (max)	5.20mm
Typical weight	23.00g
Li metal content	0.86g

MSDS as per request
Diode(1N4007, 1N5819)
PTC(SRS175...)

Tag,wire,connector,etc.available




Dimensions in mm (GB1804-m)


WARNING:

- Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
- Do Not Crush
- Do Not Dismantle
- Do Not Incinerate
- Do Not Mix New and Used Batteries
- Do Not Heat Above 100°C


1. Typical discharge profiles at 23±2°C (at mid-discharge)



2. Typical discharge profiles with different current (at discharge stable phase)



3. Storage characteristics



HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040
Tel: +86(0)27 83248452
Fax: +86(0)27 83248455

Email: haocheng@cnhcb.com
Web: www.cnhcb.com
No.: HCB-MKT.PM-S[V2.0 2018 02]