

# **Primary Lithium Battery CP603742**

3.0V [Li-MnO<sub>2</sub>]



#### BENEFITS

- High Voltage Response, Stable During Most of the Lifetime of the Application
- Energy Density up to 830Wh/L
- Wide Operating Temperature range (-40°C ~+70°C)
- Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25 C)

## **References Data**

**Nominal capacity** 

### **Electrical Characteristics**

#### **Open circuit voltage (at +25°C)**

≥3.10V

2400mAh

1200mA

#### **KEY FEATURES**

- Optimized Battery Structure, Full Discharge Capacity Maximum continuous current
- Long Endurance
- No Passivation
- GB 8897.4-2008、 IEC 60086.4:2014 and RoHS

#### MAIN APPLICATIONS

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

## 1000mA (At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity.)

different temperature, discharge current or cut-off voltage.)

#### Maximum pulse discharge current

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. The discharged capacity may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions, consult HCB.)

(At +25°C, battery discharged at continuous current 5mA until voltage reaches cut-off voltage 2.0V. The capacity can vary at

#### Storage (recommended)

(For more severe conditions, consult HCB.)

## ≤75%RH

-40°C~+70°C

≤+30°C

**Operating temperature range** (Operation above ambient temperature may lead to reduced capacity and lower voltage readings at the beginning of pulses, consult HCB.)

#### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455

Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V2.0 2018 02]




## Primary Lithium Battery CP603742

3.0V [Li-MnO<sub>2</sub>]

Physical characteristics	
Width	37.0±1.0mm
Height	42.0±1.0mm
Thickness	6.0±0.3mm
Typical weight	16.5g
Li metal content	0.84g

MSDS as per request Diode (1N4007, 1N5819) PTC (SRS175...) Tag, wire, connector, etc. available




Dimensions in mm (GB1804-m)


## WARNING:

- Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
  D
- Do Not Crush
- Do Not Dismantle
- Do Not Incinerate
- Do Not Mix New and Used Batteries
- Do Not Heat Above 100°C


## 1. Typical discharge profiles at 25°C (at mid-discharge)



2. Typical discharge profiles with different current (at discharge stable phase)



3. Storage characteristics



#### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V2.0 2018 02]